

# Product Data Sheet

## Glasroc® X Sheathing Board 12.5mm

Glasroc X Sheathing Board 12.5mm is a high performance gypsum sheathing board with mould resistant properties.

### Where to use

Use it to provide external weather protection to Steel Frame System (SFS) constructions prior to the installation of the finished exterior façade system.



## Product information

### Composition

This product is made up of a gypsum board with a glass fibre mat reinforcement which has inherent mould resistant properties. The mat protects the board with its hydrophobic coating, and has additional UV resistant properties.

### Colour

Face colour: White.  
Reverse colour: White.

### DIMENSIONS AND WEIGHTS

PRODUCT SIZES (mm)	1200 X 2400
Nominal thickness (mm)	12.5
Minimum weight (kg/m <sup>2</sup> )	10
Edge options	Square edge
Width: maximum tolerance (mm)	+0
Width: minimum tolerance (mm)	-4
Length: maximum tolerance (mm)	+0
Length: minimum tolerance (mm)	-5
Squareness: 1200mm width boards (maximum difference in diagonal measurements, mm)	5

NB: Dimensional tolerances. Quality controls are set to meet customer requirements between these maximum and minimum tolerances.

## Glasroc® X Sheathing Board 12.5mm

### Performance

Here we only provide performance information related to the product. Please see the White Book for system-dependent performance.

### Standards

EN 15283-1:2008+A1:2009, Type GM-F & GM-HI.

BBA: 17/5453.

Declarations of Performance (DoP) available [Click here](#).

Reaction to fire	A1
Thermal conductivity (W/mK)	0.1865
Water vapour permeability ( $\mu$ )	18.2
Water resistance (maximum total water absorption when tested to EN15283-1, %)	5
Mould resistance	10/10 when measured in accordance with ASTM D3273
UV resistance	No noticeable difference in colour and no degradation in surface water absorption (as measured according to EN520:2004+A1:2009) after 1000h of weathering according to ASTM G155
Moisture resistance	GM-HI
Maximum continuous temperature exposure (°C)	49

### Installation

#### Effect of condensation

The thermal insulation and ventilation requirements of national Building Regulations aim to reduce the risk of condensation and mould growth in new buildings. However, designers should take care to eliminate all possibility of problems caused by condensation, particularly in refurbishment projects.

#### Cutting

Either cut the board with a plasterboard saw, or score the front face with a sharp knife, snap it over a straightedge. Cut holes for things like socket boxes using a utility saw.

#### Jointing

To maintain optimum performance, apply Glasroc X Sealant into the joint ensuring good contact is made with the sides of the joints, and ensuring continuity of the seal where required. Tooling can be carried out within 10 minutes if necessary, using a wet tooling stick, trowel or spatula. Surplus sealant can be removed if necessary within 10 minutes using a damp cloth or sponge.

#### Screw fixing

Fix the board with the printed side facing outwards. Install fixings at least 13mm from cut edges and 10mm from bound edges. Position cut edges at internal angles wherever possible. Stagger horizontal and vertical joints between layers by at least 600mm.

#### Snagging and minor repairs

To maintain all performance requirements it will normally be necessary to replace a damaged board; please contact our Technical Support Team for specific advice.

#### Render carrier

Glasroc X is a featured component of the BBA approved weberend MT system. [Click here](#).

# Product Data Sheet

Glasroc® X Sheathing Board 12.5mm

## Sitework

### Storage

To ensure declared performance of plasterboards are not compromised they should be stored inside and kept dry. Make sure floor or ground surfaces are flat and strong enough to support them.

If plasterboards are temporarily stored outside, they should be kept clear of the ground and securely covered with an anchored polythene sheet or tarpaulin to protect from dampness and rain.

### Handling

British Gypsum fully accepts its responsibilities as a supplier of building materials and systems as required by Section 6 of the Health and Safety at Work etc. Act 1974.

To reduce manual handling risk, employers and workers should follow HSE's Manual Handling Operations Regulations 1992 (MHOR) and the HSE's guidance on manual handling at work (INDG143). Employers should carry out a risk assessment and implement control measures to avoid or minimise the need for manual handling. Workers should follow safe lifting and moving techniques and report any hazards. The 'Manual Handling Guide' published by the Gypsum Products Development Association (GDPA) and its member companies can provide additional plasterboard specific guidance and is available on the GDPA website.

Plasterboard handling should be assessed for risk before lifting or carrying. All British Gypsum plasterboards have safety information printed on the board. Where mechanical aids are available, they should be considered in the overall risk assessment.

## Safety Data Sheet

Safety Data Sheet (SDS) available. [Click here.](#)

## Packaging overview

Supplied on a reusable wooden pallet.

## Environmental

### Recyclability

You can recycle this product as long as it has minimal contamination from non-gypsum materials.

### Disposal

Segregate boards from non-gypsum waste for recycling where possible. Dispose of them according to local authority requirements.

### BES 6001 classification

Good.



"Gyproc", "Thistle", "ThistlePro", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover (French legal entity) and "Okarno" is a registered trademark of Okarno Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: british-gypsum.com. For information about products supplied by Okarno Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.