

# MATERIAL PROPERTY DATASHEET

Decorative high-pressure compact laminates according to EN 438-4:2005 of thicknesses of 13 mm (± 1/2 in) or greater for interior scientific surface solutions. Sheets consisting of layers of wood-based fibres (paper and/or wood) impregnated with thermosetting resins and surface layer(s) on one or both sides, having decorative colours or designs. A transparent topcoat is added to the surface layer(s) and cured by Trespa's unique in-house technology Electron Beam Curing (EBC), to enhance the scratch and chemical resistance. These components are bonded together with simultaneous application of heat (≥ 150° C / ≥ 302° F) and high specific pressure (> 5 MPa) to obtain a homogeneous non-porous material with increased density and integral decorative surface. They are available in the Standard grade (CGS).

PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	RESULT <sup>AB</sup>	
				STANDARD: EN 438-4	
				COLOUR/DECOR: ALL <sup>B</sup>	
<b>SURFACE QUALITY</b>					
	EN 438-2 : 4	Spots, dirt, similar surface defects	mm <sup>2</sup> /m <sup>2</sup>	≤ 1	
			in <sup>2</sup> /ft <sup>2</sup>	≤ 0.0001	
		Fibres, hairs & scratches	mm <sup>2</sup> /m <sup>2</sup>	≤ 10	
			in <sup>2</sup> /ft <sup>2</sup>	≤ 0.036	
<b>DIMENSIONAL TOLERANCES</b>					
	EN 438-2 : 5	Thickness	mm	13.0 ≤ t < 16.0: +/- 0.60	
				16.0 ≤ t < 20.0: +/- 0.70	
				20.0 ≤ t ≤ 25.0: +/- 0.80	
			in	0.4724 ≤ t < 0.6299 : +/- 0.0236	
	0.6299 ≤ t < 0.7874 : +/- 0.0275				
	EN 438-2 : 5	Thickness	mm	16.0 = t: +/- 0.70	
				20.0 = t: +/- 0.80	
			in	0.6229 = t: +/- 0.0275	
	0.7874 = t: +/- 0.0315				
	EN 438-2 : 7	Straightness of edges	mm/m	≤ 1	
			in ft	≤ 0.012	
	Trespa Standard	Squareness	mm	2550 x 1860 = max. difference between diagonals (x-y) = 4	
				3050 x 1530 = max. difference between diagonals (x-y) = 4	
			in	100.39 x 73.23 = max. difference between diagonals (x-y) = 0.1575	
	120.08 x 60.24 = max. difference between diagonals (x-y) = 0.1575				
<b>PHYSICAL PROPERTIES</b>					
Resistance to surface wear	EN 438-2 : 10	Wear resistance - Revolutions (min)	Initial point	≥ 150	
			Wear value	≥ 200	
Resistance to impact by large diameter ball	EN 438-2 : 21	Indentation diameter - $\delta \leq 1$ mm with drop height 1.8 m	mm	≤ 10	
Resistance to scratching	EN 438-2 : 25	Force	Rating (min)	≥ 4	
Resistance to dry heat (160° C / 320° F)	EN 438-2 : 16	Appearance	Rating (min)	≥ 4	
Resistance to wet heat (100° C / 212° F)	EN 438-2 : 18	Appearance	Rating (min)	≥ 4	
Dimensional stability at elevated temperature	EN 438-2 : 17	Cumulative dimensional change	Longitudinal %	≤ 0.25	
			Transversal %	≤ 0.25	
Light fastness (xenon arc)	EN 438-2 : 27	Contrast	Grey scale ISO 105 A02	≥ 6	
Resistance to water vapour	EN 438-2 : 14	Appearance	Rating (min)	≥ 4	
Resistance to crazing	EN 438-2 : 24	Appearance	Rating (min)	≥ 4	
Modulus of elasticity	EN ISO 178	Stress	MPa	≥ 9000	
Flexural strength	EN ISO 178	Stress	MPa	≥ 100	
Tensile strength	EN ISO 527-2	Stress	MPa	≥ 70	
Density	EN ISO 1183	Density	g/cm <sup>3</sup>	≥ 1.35	
<b>OTHER PROPERTIES</b>					
Release of formaldehyde	EN 717-2	Classification	Class	E1	
Chemical resistance	SEFA3-2010	Classification	Rating	Pass	

<sup>A</sup> Due to conversion from metric values, the US values provided are approximate.

<sup>B</sup> All data are related to the products mentioned in the Trespa® Toplab<sup>PLUS</sup> standard delivery programme.